



FIJA+PLUS CH-140

DESCRIPTION

Water and synthetic resin based, high-viscosity, high initial grab, assembly adhesive.

PROPERTIES

- ✓ Application temperature between +5°C and +35°C
- ✓ High quality
- ✓ High solids content
- ✓ High viscosity
- ✓ Does not string
- ✓ Instant initial grab
- ✓ Odorless
- ✓ Solvent and silicone free
- ✓ Fast cure
- ✓ One of the surfaces must be porous

APPLICATIONS

- Installation of baseboards, moldings, lined cabinets.
- Bonding of materials such as wood, concrete, polystyrene, plastics (except PE, Teflon, PP)



| Packaging | Capacity | Box quantity | Best before |
|------------|----------|--------------|-------------|
| Cartridges | 300 ml | 12 units | 5 years |
| Tube | 180 gr | 12 units | 5 years |

q

U

d

S

a

С

0

m





TECHNICAL INFORMATION

| Properties | Method | Unit | Value |
|------------------|-----------|-------------------|-------------------|
| Consistency | | | Thixotropic paste |
| Solids content | UNE 53356 | % | 64 |
| Sagging | UNE 53623 | mm | 0 |
| рН | ISO1148 | | 7 |
| Tensile strength | EN 205 | N/mm ² | 7 ± 2 |
| Density | | g/ml | 1,21 |

DIRECTIONS FOR USE

The joint surfaces must be clean and dry. Cut off the cartridge seal, cut nozzle at a 45-degree angle to required bead size and screw it on the cartridge.

Apply a continuous bead onto one of the supports to be bonded in a zigzag pattern or in spots. Press uniformly.

One of the surfaces to be bonded must be porous.

ADHESION

Excellent adhesion on most porous construction materials, all types of wood, polystyrene, plastics except PE, PP, Teflon, stone, moldings.

One of the surfaces to be bonded must be porous.

CLEANING

Uncured product can be cleaned with water. Once cured, the product can be removed mechanically.

RECOMMENDED ACCESSORIES

Applicator gun P-1441



HEALTH AND SAFETY

Safety data sheet available upon request of the client.

<u>Note</u>

The information contained in this document, as well as our technical advice whether verbal or written, is the result of our experience with the product and should be considered as collaboration without compromise, since the use and / or final application of our adhesives is beyond our control, declining all liability for improper use. The customer is responsible to confirm and evaluate prior to use, by trial or test the product conforms to required employment. So our guarantee is limited to ensure the quality of our products, according to our quality standards.

Quiadsa reserves the right to change the properties of its products. Users must know and use the latest updated version of the technical data sheets, Quiadsa will send them upon request or they can be downloaded on the website: www.quiadsa.com

m

Date: 12/06/2019 Edition: 5